Technical Data Sheet Code 613 Ref. 1909

COLORGUM 100

FINISHING BASED ON PURE CHLORINATED RUBBER AND PLASTIFYING AGENTS FOR SWIMMINGPOOLS, FLOORS AND WATERPROOFING WORK AND MAINTENANCE OF SURFACES THAT COME IN CONTACT WITH WATER.

TYPE OF BINDER	Pure chlorinated rubber
ASPECT OF DRY FILM	Glossy – 80 gloss
AVAILABLE COLOURS	Light-blue, normal and bright RAL shades and UNISYSTEM tinting system
SPECIFIC WEIGHT	1,410 kg / lt + / - 0,05 at 20° C
VISCOSITY	22" ford viscosity cup F8 +/- 2" at 20º C
APPLICATION (5°C ≤ T ≤ 30°C)	Brush – Roller - Spray
DILUTION	1° coat: 15% SINTESOL 2° - 3° coat: 10% SINTESOL
APPROXIMATE YIELD	5 – 6 sqm/Kg per coat
DRYING at 20°C	Out of dust: 5 minutes / Touch dry: 20-30 minutes / Thoroughly dry: 24 hours
OVERCOATING INTERVAL	24 hours
STORAGE AND SHELF LIFE	Store in a cool, dry, well ventilated area away from heat and direct sunlight. The product has a shelf life of 12 months when kept in original sealed packaging. It must be protected from frost.

CHARACTERISTICS AND FIELD OF APPLICATION

It is suitable for pools, cement tanks and any other iron surfaces exposed to atmospheric agents for long period of time. It is absolutely necessary for painting pools and tanks that have been previously treated with vinyl chloride or chlorinated rubber products. It is ideal for maintenance of surfaces that come in contact with water. Not suitable for industrial floors with high traffic.

SUBSTRATE PREPARATION

NEW POOLS: wash with **CLOROFOND** before application. Wash again with fresh water, empty the tub and let it dry.
POOLS WITH EXISTING PAINTWORK: remove anything that is not perfectly anchored to the substrate. Sand existing paintworks and then apply the new finishing.
In any case, the pool must be filled after the product has dried thoroughly, not earlier than a week
Ferrous material must be cleaned, dried, degreased and rust free.
CONCRETE FLOORS: the substrate must be cleaned, degreased and free from moisture spots.
Ensure possible sanding for smooth and slightly porous floors, or for floors with existing paintwork.

WARNINGS

Apply the product in the climatic conditions as mentioned above. Inappropriate conditions of application of the product are adversely affected in the drying time and the achievement of the optimum appearance and performance can be compromised. Drying may take longer when temperatures are lower and humidity is higher and some unsightly looking, translucent and sticky drops could appear.

The product complies with C.L.P. European Regulation, in force from 1st June 2015.

All our products are of a high quality and subject to rigid quality control. The information given in this specification sheet is for guidance and is given in good faith but no liability can be assumed by Barozzi Vernici S.r.l. for the performance of the products and for final results, since skills of application and site conditions are beyond our direct control. The information contained in this document is strictly confidential and shall be the sole and exclusive property of Barozzi Vernici S.r.l..