

## **INTERAMIANTO 257 – 000 Ready to use**

**INSULATING – FIXATIVE – ENCAPSULATION TYPE D FOR THE REMOVAL OF CONCRETE-ASBESTOS.**

<b>TYPE OF BINDER</b>	Modified synthetic dispersion
<b>ASPECT OF DRY FILM</b>	Semi-transparent
<b>AVAILABLE COLOURS</b>	Red (TC6319), transparent green and other colours on request
<b>SPECIFIC WEIGHT</b>	1,02 kg/lit +/- 0,03 at 20° C
<b>VISCOSITY</b>	15" with ford viscosity cup F4 +/- 2" at 20° C
<b>APPLICATION (5°C ≤ T ≤ 30°C)</b>	Brush – Roller – Spray without pressure ("airless" type)
<b>DILUTION</b>	Ready to use, do not thin
<b>APPROXIMATE YIELD</b>	200 ÷ 250 gr/sqm with not thinned product
<b>DRYING at 20°C</b>	Touch dry: 10 – 15 minutes / Thoroughly dry: 4 – 6 hours
<b>OVERCOATING INTERVAL</b>	4 – 6 hours
<b>V.O.C CONTENT</b>	Less than 30 gr/lit [Directive 2004/42/CE: (cat. A/h WB: 30)]
<b>STORAGE AND SHELF LIFE</b>	Store in a cool, dry, well ventilated area away from heat and direct sunlight. The product has a shelf life of 12 months when kept in original sealed packaging. It must be protected from frost.

### **CHARACTERISTICS AND FIELD OF APPLICATION**

**INTERAMIANTO 257 - 000 Ready to use** is suitable as insulating fixative of concrete-asbestos roofs, prefabricated panels, etc., for TYPE D INTERVENTIONS. The product carries out a temporary encapsulation, as specified in the attachments and appendices of the Italian Ministerial Decree 20<sup>th</sup> August 1999. Do not apply in adverse climatic conditions or with impending rain. Yield changes according to the absorption capacity and to the state of deterioration of the surface.

Declaration of product conformity (self-certification suitable for TYPE D interventions) and relative material safety data sheet are available. Wash tools with water. For further information contact our technical office.

### **SUBSTRATE PREPARATION**

The concrete-asbestos surface must be clean and dry (according with directions of Italian Ministerial Decree 20<sup>th</sup> August 1999).

Apply one coat of **INTERAMIANTO 257 - 000 Ready to use** and after some hours drying, apply a second coat till reaching a dry film of 80 ÷ 120 µ.

### **WARNINGS**

Apply the product in climatic conditions as mentioned above. In unsuitable conditions, the application of the product is adversely affected in the drying time, and the achievement of the optimum appearance and performance can be compromised.

The product complies with C.L.P. European Regulation, in force from 1<sup>st</sup> June 2015.

*All our products are of a high quality and subject to rigid quality control. The information given in this specification sheet is for guidance and is given in good faith but no liability can be assumed by Barozzi Vernici S.r.l. for the performance of the products and for final results, since skills of application and site conditions are beyond our direct control. The information contained in this document is strictly confidential and shall be the sole and exclusive property of Barozzi Vernici S.r.l..*