



## **MAGNUM 5 STELLE filling**

**ACRYLIC-QUARTZ, ANTI-ALGAE WATER-BASED, FILLING PAINT FOR EXTERIORS.  
MODERATELY ELASTIC, HIGHLY COVERING AND WITH HIGH YIELD.**

<b>TYPE OF BINDER</b>	Modified pure acrylic
<b>ASPECT OF DRY FILM</b>	Matt, rough
<b>AVAILABLE COLOURS</b>	White and UNISYSTEM tinting system
<b>SPECIFIC WEIGHT</b>	1,50 kg/lt +/- 0,05 at 20° C
<b>VISCOSITY</b>	14.000/ cps +/- 2000 (A6 V20 BROOKFIELD at 20° C)
<b>APPLICATION (5°C ≤ T ≤ 30°C)</b>	Brush – Roller
<b>DILUTION</b>	Brush: 20% with clear water / Roller: 15 – 20 % with clear water
<b>APPROXIMATE YIELD</b>	7 - 8 sqm/lt per coat
<b>DRYING at 20°C</b>	Out of dust: 5 minutes / Touch dry: 10 – 15 minutes / Thoroughly dry: 2 – 4 hours
<b>OVERCOATING INTERVAL</b>	4 - 6 hours
<b>V.O.C CONTENT</b>	Less than 40 gr/lt [Directive 2004/42/CE: (cat. A/c WB: 40)]
<b>STORAGE AND SHELF LIFE</b>	Store in a cool, dry, well ventilated area away from heat and direct sunlight. The product has a shelf life of 12 months when kept in original sealed packaging. It must be protected from frost.

### **CHARACTERISTICS AND FIELD OF APPLICATION**

It is suitable for the building sector as acrylic, washable, quartz, anti-algae and moderately elastic paint. Because of its high resistance and non-yellowing properties, it is used for protecting private houses, both new and already painted.

Diluted product must be used within 2-3 days.

### **SUBSTRATE PREPARATION**

**NEW WALLS:** the wall must be dry, clean and free of any impurities, including sand which is not completely attached. It is recommended to apply one coat of fixative **NANOFIX** which increases the adherence, eliminates surface pulverization and makes the absorption of the substrate uniform. It also reduces spot-formation and paint consumption.

**WALLS WITH EXISTING PAINTWORK:** remove old detaching paints by scraping, brushing or by stripping, if necessary. In case of dirt and moulds ensure suitable treatment with high-pressure washer and then apply **LINDOSTOP**.

Apply the first coat of **MAGNUM 5 STELLE filling** more diluted than the following one, in order to improve the penetration of the paint into the substrate.

### **WARNINGS**

Apply the product in climatic conditions as mentioned above. In unsuitable conditions, the application of the product is adversely affected in the drying time, and the achievement of the optimum appearance and performance can be compromised. In ideal weather conditions (+20°C. and 65% R.H.) drying and physical cross linking occurs in about 7 days; yet, drying may take longer when temperatures are lower and humidity is higher and some unsightly looking, translucent and sticky leakages could appear. This temporary phenomenon does not affect the performance of the product and may be removed by washing or waiting for the next rainfall event. Not mature plasters and patches can cause fading, stains and appearing of efflorescence. The physiological deterioration of the product or its colour over time is not a sign of non-conformity of it.

The product complies with C.L.P. European Regulation, in force from 1<sup>st</sup> June 2015.

*All our products are of a high quality and subject to rigid quality control. The information given in this specification sheet is for guidance and is given in good faith but no liability can be assumed by Barozzi Vernici S.r.l. for the performance of the products and for final results, since skills of application and site conditions are beyond our direct control. The information contained in this document is strictly confidential and shall be the sole and exclusive property of Barozzi Vernici S.r.l.*

