NERO IMPERIAL "catramina"

BLACK OIL-BITUMINOUS VARNISH FOR IRON, SCAFFOLDS, PIPES AND UNDERGROUND TANKS.

TYPE OF BINDER	Oxidized bitumen and plasticizers
ASPECT OF DRY FILM	Glossy
AVAILABLE COLOURS	Shiny black
SPECIFIC WEIGHT	0,96 kg/lt +/- 0,04 at 20° C
VISCOSITY	56-74" ford viscosity cup F4 at 25° C
APPLICATION (5°C ≤ T ≤ 35°C)	Brush – Spray – Dipping
DILUTION	Spray: with NITROSOL/SINTESOL just enough Brush: 5% - 10% SINTESOL
APPROXIMATE YIELD	7 – 8 sqm/kg according to the thickness applied
DRYING at 20°C	Out of dust: 50 – 60 minutes / Touch dry: 4 – 5 hours / Thoroughly dry: 36 – 48 hours
OVERCOATING INTERVAL	24 – 36 hours
V.O.C CONTENT	Less than 400 gr/lt [Directive 2004/42/CE: (cat. A/h SB: 750)]
STORAGE AND SHELF LIFE	Store in a cool, dry, well ventilated area away from heat and direct sunlight. The product has a shelf life of 12 months when kept in original sealed packaging. It must be protected from frost.

CHARACTERISTICS AND FIELD OF APPLICATION

It serves as a protection for tanks, iron pipes or wooden posts that go in the ground. The product is durable, even if used outside; however, the thermoplasticity of the bitumen, which is very sensitive to temperature changes, must be taken into account. Therefore, the cold could cause craks and hot temperatures could soften it.

SUBSTRATE PREPARATION

IRON: the surface must be cleaned, dried, degreased and free from rust and/or scale.
WOOD: it must be perfectly clean and dry.

WARNINGS

Apply the product in the climatic conditions as mentioned above. Inappropriate conditions of application of the product are adversely affected in the drying time and the achievement of the optimum appearance and performance can be compromised. Drying may take longer when temperatures are lower and humidity is higher and some unsightly looking, translucent and sticky drops could appear.

The product complies with C.L.P. European Regulation, in force from 1st June 2015.

All our products are of a high quality and subject to rigid quality control. The information given in this specification sheet is for guidance and is given in good faith but no liability can be assumed by Barozzi Vernici S.r.l. for the performance of the products and for final results, since skills of application and site conditions are beyond our direct control. The information contained in this document is strictly confidential and shall be the sole and exclusive property of Barozzi Vernici S.r.l..